

## Resist 86

### Product description

This is a two component moisture curing inorganic zinc ethyl silicate coating. It is a fast curing, very high zinc dust containing product. It conforms to the compositional requirements of SSPC paint 20, level 1, ISO 12944-5 and AS/NZS 3750.15 1994. It provides excellent corrosion protection as a single coat or as part of a complete coating system. It is heat resistant up to 540 °C (1004 °F). To be used as primer in a coating system and as single coat system in atmospheric environments. Suitable for properly prepared carbon steel substrates only. This product complies with ASTM D520 type II zinc dust.

### Typical use

Protective:

Suitable for structural steel and piping to be exposed to highly corrosive environments, C5I or C5M (ISO 12944-2). Recommended for offshore environments, refineries, power plants, bridges, buildings, mining equipment and general structural steel. Specially designed as a primer for coating systems where extended durability is required.

### Approvals and certificates

Pre-qualified in accordance with NORSOK M-501 in selected systems

Suitable for use in mating surfaces of High Strength Friction Grip Bolted Connections:

Complies with the requirements of Research Council on Structural Connections (RCSC) Class B, Appendix A (Slip coefficient and resistance to tension creep).

Additional certificates and approvals may be available on request.

### Colours

greenish grey, grey

### Product data

| Property              | Test/Standard        | Description |
|-----------------------|----------------------|-------------|
| Solids by volume      | OCCA Monograph No. 4 | 67 ± 2 %    |
| Gloss level (GU 60 °) | ISO 2813             | matt (0-35) |
| Flash point           | ISO 3679 Method 1    | 14 °C       |
| Density               | calculated           | 2.6 kg/l    |

| Region    | Regulation  | Test Standard       | VOC Value |
|-----------|---|---------------------|-----------|
| US        | CARB(SCM)2020 / SCAQMD rule 1113  | US EPA Method 24    | 455 g/l   |
| Hong Kong | Air Pollution Control (VOC) Regulation                                      | US EPA Method 24    | 455 g/l   |
| EU        | European Paint Directive 2004/42/CE   | Calculated          | 509 g/l   |
| EU IED    | Industrial Emission Directive 2010/75/EU                                    | Calculated          | 509 g/l   |
| Korea     | Korea Clean Air Conservation Act  | KS M ISO 11890-1    | 499 g/l   |
| China     | GB 30981-2020 Limit of harmful substances of industrial protective coatings | GB/T 23985-2009 8.3 | 431 g/l   |

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

|                            |            |                   |
|----------------------------|------------|-------------------|
| Dry film thickness         | 50 - 90    | µm                |
| Wet film thickness         | 75 - 135   | µm                |
| Theoretical spreading rate | 13.4 - 7.4 | m <sup>2</sup> /l |

## Surface preparation

### Surface preparation summary table

| Substrate    | Surface preparation   |   |
|--------------|---|---|
|              | Minimum   | Recommended   |
| Carbon steel | Sa 2½ (ISO 8501-1) with a surface profile Fine to Medium G (ISO 8503-2) | Sa 2½ (ISO 8501-1) with a surface profile Fine to Medium G (ISO 8503-2) |

## Application

### Application methods

The product can be applied by

|        |   |
|--------|---|
| Spray: | Use air spray or airless spray.   |
| Brush: | Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness. In order to avoid settling of heavy zinc, continuous mechanical stirring during application is recommended. |

### Product mixing ratio (by volume)

|                       |             |
|-----------------------|-------------|
| Resist 86 Comp A      | 8 part(s)   |
| Jotun Zinc 100 Comp B | 2.6 part(s) |

Component A is a liquid and Component B is dry zinc dust. Component A must be well shaken before use. Pour the zinc dust slowly into the liquid during mechanical mixing. Stir until lump free and pass through a 60 mesh sieve.

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 4 / Jotun Thinner No. 25

Thinning max.: 5 %

Jotun Thinner No. 4: for fast evaporation  
Jotun Thinner No. 25: for slow evaporation

Jotun Thinner No. 28 can be used as alternative to Jotun Thinner No. 4 for fast evaporation.

Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation. **Note:** Korean VOC regulation "Korea Clean Air Conservation Act" and its corresponding thinning limit will prevail over recommended thinning volumes.

Jotun Thinner No. 17 can be used as alternative cleaning solvent.

### Guiding data for airless spray

|                               |                  |
|-------------------------------|------------------|
| Nozzle tip (inch/1000):       | 17-21            |
| Pressure at nozzle (minimum): | 100 bar/1400 psi |

## Drying and Curing time

| Substrate temperature     | 5 °C  | 10 °C  | 23 °C  | 40 °C  |
|---------------------------|-------|--------|--------|--------|
| Surface (touch) dry       | 1 h   | 30 min | 15 min | 13 min |
| Walk-on-dry               | 1.5 h | 45 min | 30 min | 25 min |
| Dry to over coat, minimum | 18 h  | 13 h   | 4 h    | 1.5 h  |
| Dried/cured for service   | 18 h  | 13 h   | 4 h    | 1.5 h  |

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

The drying and curing times, as well as over coating intervals for inorganic zinc ethyl silicates are measured under controlled temperatures, relative humidity (RH) 70 % during application and curing, and at average of the DFT range for the product. Higher RH will increase the curing speed.

At application below 60% RH curing will be retarded. Jotun Zinc 100 LHA can be used to speed up curing. Refer to the Application Guide (AG) for additional information.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

|                   |       |
|-------------------|-------|
| Paint temperature | 23 °C |
| Pot life          | 8 h   |

## Heat resistance

|                  | Temperature |        |
|------------------|-------------|--------|
|                  | Continuous  | Peak   |
| Dry, atmospheric | 400 °C      | 540 °C |

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

**This product can withstand exposure to dry temperature from 400°C up to 540 °C (1004 °F) for a longer period if applied at 50µm DFT and topcoated with a suitable product. Recommended inorganic zinc ethyl silicate coating with better durability for those temperatures is Jotatemp 540 Zinc.**

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Subsequent coat: epoxy, silicone acrylic

## Packaging (typical)

|                       | Volume<br>(litres) | Size of containers<br>(litres) |
|-----------------------|--------------------|--------------------------------|
| Resist 86 Comp A      | 8                  | 10                             |
| Jotun Zinc 100 Comp B | 2.6                | 20                             |

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### Shelf life at 23 °C

|                       |             |
|-----------------------|-------------|
| Resist 86 Comp A      | 6 month(s)  |
| Jotun Zinc 100 Comp B | 48 month(s) |

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Environmental Documentation

This product can contribute to Green Building Standard credits. Please refer to Jotun.com for more information or contact your local Jotun representative.

Environmental Product Declaration (EPD) is available at [www.epd-norge.no](http://www.epd-norge.no)

## Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## Colour variation

When applicable, products primarily meant for use as primers or antifouling may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.